


approved Journal

Open Access, Peer Review and refereed journal, journal of, indexing index journal

jetir.org

OPEN

International Journal of Engineering and Technology Innovation









Country	Taiwan -  SJR Ranking of Taiwan	<div>6</div> <div>H Index</div>
Subject Area and Category	Engineering Civil and Structural Engineering Electrical and Electronic Engineering Mechanical Engineering Mechanics of Materials	
Publisher	Taiwan Association of Engineering and Technology Innovation	
Publication type	Journals	
ISSN	2226809X, 22235329	
Coverage	2015-2020	
Scope	The IJETI journal focus on the field of engineering and technology Innovation. And it publishes original papers including but not limited to the following fields: Automation Engineering Civil Engineering Control Engineering Electric Engineering Electronic Engineering Green Technology Information Engineering Mechanical Engineering Material Engineering Mechatronics and Robotics Engineering Nanotechnology Optic Engineering Sport Science and Technology Innovation Management Other Engineering and Technology Related Topics.	
	Homepage	
	How to publish in this journal	
	Contact	
	 Join the conversation about this journal	

IJENS Journals

IJENS publisher SCOPUS - indexed; Call For Papers

ijens.org

OPEN



Show this widget in your own website

Just copy the code below and paste within your html code:

`<a href="https://www.scimagojr.com/journalsearch.php?q=21100406800&tip=sid&clean=0"`



N **Neha Singh** 3 months ago

hii..

- 1.how much time does it takes to publish?
2. how much money?
3. acceptance rate?

reply



Melanie Ortiz 3 months ago

SCImago Team

Dear Neha,

thank you for contacting us.

We are sorry to tell you that SCImago Journal & Country Rank is not a journal. SJR is a portal with scientometric indicators of journals indexed in Elsevier/Scopus.

Unfortunately, we cannot help you with your request, we suggest you to visit the journal's homepage or contact the journal's editorial staff , so they could inform you more deeply.

Best Regards, SCImago Team

Y **Yousif Alyousifi** 6 months ago

Hi

Is this journal still indexed by SCOPUS IN 2020?

reply



Melanie Ortiz 5 months ago

SCImago Team

Dear Yousif, thank you very much for your comment, unfortunately we cannot help you with your request. We suggest you to consult the Scopus database directly. Remember that the SJR is a static image of a database (Scopus) which is changing every day. Best regards, SCImago Team



[Home](#) [Editorial Board](#) [Manuscript Submission](#) [Focus And Scope](#) [Review Process](#) [News](#) [Contact Us](#)

Journal Menu

- ▶ Current Issue
- ▶ Archive
- ▶ Special Issues
- ▶ In Press
- ▶ Author's Instruction
- ▶ Publication Ethics and Malpractice
- ▶ Digital Preservation Policy
- ▶ Copyright Notice
- ▶ Indexing
- ▶ FAQ

1.7 CiteScore
40th percentile
Powered by Scopus

SJR 2019
0.208

SNIP 2019
0.924

Related Links

- ▶ TAETI Association
- ▶ Conferences
- ▶ Journals

84457
W3 Counter

Starting date: Dec. 21, 2015

Visitors	
48,415	2,527
10,544	2,069
5,291	2,066
5,286	1,904
2,800	1,882

FLAG counter

HOT [News] New Issue, Vol. 10, No. 3, has been published.

HOME

International Journal of Engineering and Technology Innovation(IJETI), ISSN 2223-5329 (Print), ISSN 2226-809X (Online), is an international, multidiscipline, peer-reviewed scholarly journal, published quarterly for researchers, developers, technical managers, and educators in the field of engineering and technology innovation. Articles of original research, reports, reviews, and commentaries are welcomed by IJETI. The goal of this journal is to provide a platform for scientists and academicians all over the world to promote, share, and discuss various new issues and developments in all areas of engineering and technology innovation.

Currently, there is no any charge for the papers submitted to IJETI. All manuscripts must be prepared in English, and are subject to a rigorous and fair peer-review process. Decisions will be made as rapidly as possible. Since IJETI is an open access journal, all accepted papers will immediately appear online. The journal publishes original papers including but not limited to the following fields:

- Automation Engineering
- Civil Engineering
- Control Engineering
- Electric Engineering
- Electronic Engineering
- Green Technology
- Information Engineering
- Mechanical Engineering
- Material Engineering
- Mechatronics and Robotics Engineering
- Nanotechnology
- Optic Engineering
- Sport Science and Technology
- Innovation Management
- Other Engineering and Technology Related Topics





[Home](#) [Editorial Board](#) [Manuscript Submission](#) [Focus And Scope](#) [Review Process](#) [News](#) [Contact Us](#)

Journal Menu

- ▶ [Current Issue](#)
- ▶ [Archive](#)
- ▶ [Special Issues](#)
- ▶ [In Press](#)
- ▶ [Author's Instruction](#)
- ▶ [Publication Ethics and Malpractice](#)
- ▶ [Digital Preservation Policy](#)
- ▶ [Copyright Notice](#)
- ▶ [Indexing](#)
- ▶ [FAQ](#)

1.7
CiteScore
40th percentile
Powered by Scopus

SJR 2019
0.208

SNIP 2019
0.924

Related Links

- ▶ [TAETI Association](#)
- ▶ [Conferences](#)
- ▶ [Journals](#)

84457
V3 Counter

Starting date: Dec. 21, 2015



Editorial board

Honorary Editor

- J. S. Rao, Kumaraguru College of Technology, India

Editor-in-Chief

- Wen-Hsiang Hsieh, National Formosa University, Taiwan

Associate Editor-in-Chief:

- Felipe Lare-Rosano, National University of Mexico, Mexico
- Vagn Steen Gruner Hanson, Danish Technical University, Denmark
- Yunn-Lin Hwang, National Formosa University, Taiwan
- Zongyu Chang, Ocean University of China, P.R. China
- Ikuo Yamamoto, Nagasaki University, Japan
- Jason Shian-Ching Jang, National Central University, Taiwan

Associate Editors of Topics:

- Chun-Hui Wu, National Formosa University, Taiwan (Information management and Project management)
- E. Manske, TU Ilmenau, Germany (Precision Measurement)
- Gow-Yi Tzou, Kan Yuan University of Sciences and Technology, Taiwan (Metal Forming)
- Jin. H. Choi, KyungHee University, Korea (Multidynamics, CAE, mechatronics)
- Kin Huat Low, Nanyang Technological University, Singapore (Bionic robot, UAV)
- Minvydas Ragulskis, Kaunas University of Technology, Lithuania (Nonlinear dynamical systems, chaos, numerical simulation)
- R. S. Beniwal, CSIR- National Institute of Science Communication and Information Resources, India (Material Science and Engineering)
- Uldis Strautins, University of Latvia, Latvia. (Mathematical modeling, scientific computing, applied mathematics)
- Yi-Chang Wu, National Yunlin University of Science & Technology, Taiwan (Mechanism and Machine Theory)

Editorial Board Member:

- A. Walton, University of Edinburgh, UK
- Aylie Han, University of Diponegoro, Indonesia
- Buntara S. Gan, Nihon University, Japan
- C. Y. Chen, Far East University, Taiwan
- E. Manske, TU Ilmenau, Germany
- G. Jäger, TU Ilmenau, Germany
- H. M. Jonkers, Delft University of Technology, Netherlands
- Igor Meglinski, University of Oulu, Finland
- J. S. Dai, King's of college London, UK
- Kil Hyun Kwon, Korea Advanced Institute of Science and Technology, Korea
- M. Chang, Chung Yuan Christian University, Taiwan
- R. X. Du, The Chinese University of Hong Kong, HK
- Salah Kamel, South Valley University, Egypt
- S. C. Tzeng, Chienkuo Technology University, Taiwan
- Ahmad Zuhairi Abdullah, University of Sains Malaysia, Malaysia
- Sangkyun Kim, Kangwon National University, Korea
- Basant Lal Maheshwari, University of Western Sydney, Australia
- Alberto A. Boretti, Missouri University of Science and Technology, United States
- Ka-Veng Yuen, University of Macau, Macau
- Tat Leung Chan, Hong Kong Polytechnic University, Hong Kong
- Asit Kumar Khanra, National Institute of Technology, India
- Vo Dinh Bay, Ho Chi Minh City University of Technology, Vietnam
- Frank Tillenamp, Zürich University of Applied Sciences, Switzerland
- Anissa Eddhahak, Arts & Métiers Paris Tech, France

- Allan Nana Soriano, Mapúa Institute of Technology, Philippines
- Sikula Ondrej, Brno University of Technology, Czech
- Costel Emil Cotet, Department of Machines and Manufacturing Systems (MSP), Romania
- Reka Barabas, University Babes-Bolyai Cluj- Napoca, Romania
- Giuseppe Starace, University of Salento, Italy
- Mehdi Roopaei, University of Texas at San Antonio (UTSA), USA
- Yangzhi Chen, South China University of Technology, P.R. China
- Jose A Garza-Reyes, The University of Derby, UK
- Yufeng Yao, University of the West of England, UK
- Haim Abramovich, Faculty of Aerospace Engineering, Technion-Israel Institute of Technology, Isarel
- Faris Ali, School of the Built Environment, University of Ulster, UK
- Abdeltif Amrane, Universite de Rennes 1, France
- Daniel Cozzolino, School of Science, RMIT University, Melbourne, Australia
- Mahmoud Bayat, Department of Mechanical Engineering and Materials Science, University of Pittsburgh, USA
- Roberto Citarella, Department of Industrial Engineering, University of Salerno, Italy
- Paolino Di Felice, Department of Industrial and Information Engineering and Economics, University of L'Aquila, Italy
- Supriyo Bandyopadhyay, Electrical and Computer Engineering, Virginia Commonwealth University, USA
- Alberto Doria, Department of Industrial Engineering, University of Padova, Italy
- Gautam Srivastava, Brandon University, Canada
- Alberto Benato, Department of Industrial Engineering, University of Padova, Padova, Italy
- Luigi Fortuna, Department of Electrical, Electronics and Computer Engineering (DIEEI), University of Catania, Italy
- Antonio Ficarella, Department of Engineering for Innovation, University of Salento, Italy
- Zong Woo Geem, College of Information Technology, Gachon University, Korea
- Mark Jackson, School of Interdisciplinary Studies, College of Technology and Aviation, Kansas State University, USA
- Gilsoo Jang, School of Electrical Engineering, Korea University, Korea
- Mohamed Khayet, Department of Structure of Matter, Thermal Physics and Electronics Faculty of Physics, University Complutense of Madrid Avda., Spain
- Caterina Ciminelli, Electrical and Information Engineering Department, Polytechnic University of Bari, Italy
- Nir Krakauer, Department of Civil Engineering, City College of New York, USA
- Motoharu Fujigaki, Human and Artificial Intelligent Systems, Graduate School of Engineering, University of Fukui, Japan
- Enrico Drioli, Institute on Membrane Technology (CNR-ITM) c/o, School of Engineering, University of Calabria, Italy
- Michalis Konsolakis, School of Production Engineering and Management, Technical University of Crete, Greece
- Sophie Laurent, Organic and Biomedical Chemistry Unit, NMR and Molecular Imaging laboratory, University of Mons, Belgium
- N.C. Markatos, Department of Chemical Engineering, National Technical University of Athens, Greece
- Simona Silvia Merola, Istituto Motori, National Research Council, Italy
- Emilio Martines, Consorzio RFX, Italy
- Xiaochun Cheng, Department of Computer Science, Middlesex University, UK
- Weimin Huang, School of Mechanical and Aerospace Engineering, Nanyang Technological University, Singapore
- Gianluca Cicala, Department of Civil Engineering and Architecture, University of Catania, Italy
- Vicente Compan Moreno, Department of Applied Thermodynamics, Polytechnic University of Valencia, Spain
- Iolanda De Marco, Industrial Engineering Department, University of Salerno, Italy
- T M Indra Mahlia, School of Information, Systems and Modelling, University of Technology Sydney, Australia
- Alessandro Pistone, Department of Engineering, University of Messina, Italy
- Haw-Ming Huang, Taipei Medical University, Taipei, Taiwan
- Paolo Di Giamberardino, Department of Computer, Control and Management Engineering, Sapienza University of Rome, Italy
- Md Arafatur Rahman, Faculty of Computing, University Malaysia Pahang, Malaysia
- Dushantha Nalin K. Jayakody, School of Computer Science and Robotics, National Research Tomsk Polytechnic University, Russia
- Zoran H. Peric, Faculty of Electronic Engineering, University of Nis, Serbia

Assistant Editor

- S. W. Lin, Taiwan Association of Engineering and Technology Innovation, Taiwan



[Home](#) [Editorial Board](#) [Manuscript Submission](#) [Focus And Scope](#) [Review Process](#) [News](#) [Contact Us](#)

Journal Menu

- ▶ Current Issue
- ▶ Archive
- ▶ Special Issues
- ▶ In Press
- ▶ Author's Instruction
- ▶ Publication Ethics and Malpractice
- ▶ Digital Preservation Policy
- ▶ Copyright Notice
- ▶ Indexing
- ▶ FAQ

1.7
40th percentile
Powered by Scopus

SJR 2019
0.208

SNIP 2019
0.924

Related Links

- ▶ TAETI Association
- ▶ Conferences
- ▶ Journals

84456
V3 Counter

Starting date: Dec. 21, 2015

Visitors	
	48,415
	10,544
	5,291
	2,066
	5,286
	1,904
	2,800
	1,882

FLAG counter


International Journal of Engineering and Technology Innovation

(IJETI, ISSN Print 2223-5329, ISSN Online 2226-809X)

Vol. 10, No. 3

July 2020

CONTENTS



- 165-178 **Using a Hybrid Evolutionary Algorithm for Solving Signal Transmission Station Location and Allocation Problem with Different Regional Communication Quality Restriction**

Ta-Cheng Chen, Sheng-Chuan Wang, Wen-Cheng Tseng

Abstract and References: [PDF](#), Full Paper: [PDF](#), Download: [243](#)



- 179-190 **Machining Parameter Optimization of EVA Foam Orthotic Shoe**

Insoles

Paulus Wisnu Anggoro, Abet Adhy Anthony, Mohammad

Tauviqirrahman, Jamari, Athanasius Priharyoto Bayuseno, Aylie Han


Abstract and References: [PDF](#), Full Paper: [PDF](#), Download: [201](#)



- 191-199 **Engineering Properties of Ternary Cementless Blended Materials**

Wei-Ting Lin, Kinga Korniejenko, Marek Hebda, Michał Łach, Janusz Mikula


Abstract and References: [PDF](#), Full Paper: [PDF](#), Download: [128](#)



- 200-210 **Cross Layer Based Cooperative Communication Protocol for Improving Network Performance in Underwater Sensor Networks**

Kihyun Kim, Sunmyeng Kim

Abstract and References: [PDF](#), Full Paper: [PDF](#), Download: [137](#)



- 211-224 **Experimental Investigation of Impacting Flow between a Sub-Scale Twin-Rotor Configuration**

Ali Mehrabi, Ali Reza Davari

Abstract and References: [PDF](#), Full Paper: [PDF](#), Download: [160](#)



- 225-234 **An RGB-NIR Image Fusion Method for Improving Feature Matching**

Hanhoon Park

Abstract and References: [PDF](#), Full Paper: [PDF](#), Download: [132](#)

Machining Parameter Optimization of EVA Foam Orthotic Shoe Insoles

Paulus Wisnu Anggoro^{1,*}, Abet Adhy Anthony¹, Mohammad Tauviquirrahman², Jamari²,
Athanasius Priharyoto Bayuseno², Aylie Han³

¹Department of Industrial Engineering, University of Atma Jaya Yogyakarta, D.I. Yogyakarta, Indonesia

²Department of Mechanical Engineering, University of Diponegoro, Semarang, Central Java, Indonesia

³Department of Civil Engineering, University of Diponegoro, Semarang, Central Java, Indonesia

Received 16 December 2019; received in revised form 03 March 2020; accepted 19 May 2020

DOI: <https://doi.org/10.46604/ijeti.2020.5099>

Abstract

In this study, ethylene-vinyl acetate (EVA) foam orthotic shoe insoles with different surface roughnesses (Ra) are investigated in terms of CNC milling strategy. Based on a hybrid Taguchi-response surface methodology (TM-RSM) approach, machining parameters, including tool path strategy, spindle speed, feed rate, and step over, as well as material hardness, are of particular interest. The main aim of this work is to develop mathematical models and determine the optimum machining parameters. Experiments are conducted on a CNC milling machine with a standard milling cutter and run under dry coolants. The optimal conditions are established based on TM and then used to determine the optimum values in the RSM modeling. The main finding of the present work is that there are significant improvements in the Ra, by up 0.24% and 4.13%, and machining time, by up 0.43% and 0.41%, obtained with TM-RSM in comparison to TM analysis.

Keywords: shoe insole, EVA foam, CNC milling, surface roughness (Ra), machining time

1. Introduction

There are three types of shoe soles: the bottom of the shoe that contacts directly with the ground (outsole), the bottom of the shoes attached to the outsole, and the insole is the inside of the shoe that contacts directly with the patient's feet. Among them, the second provides comfort to the foot during exertion (middle sole), and the insole of the third is located on the inside of the shoe between the outsole and upper shoe. The shoe insole is in direct contact with the human foot while doing daily activities such as walking, running, and jumping. This part is very important in determining whether the user or patient feels comfortable when wearing shoes.

Types of rubber include isobutylene-isoprene rubber, chloroprene rubber, nitrile rubber, silicone rubber, polyurethane, natural rubber, ethylene-propylene rubber, and polybutadiene [1]. While the rubber materials were used as orthotic shoe insoles in the manufacturing industry for EVA, some researchers [2-7] reported that EVA foam shaped like a rubber material, known as EVA foam rubber, is also a popular raw material for insole shoe orthotics (ISO) in the shoe industry. This material proved widely used in the engineering design process for shoe insole manufacturing because of useful properties including good elastomer properties, lightweight, formability, and quite easily processed manufacturing on CNC milling machines. EVA foam rubber is a copolymer formed from the monomers ethylene and vinyl acetate (VA) with resin and rubber [8]. EVA rubber foam also has many applications in sports and medical engineering because it is very good as an energy absorber and has a high fracture toughness relative to other polymers [9]. Besides, this material is consistently used in advanced composites for

* Corresponding author. E-mail address: pauluswisnuanggoro@gmail.com

Tel.: +62-857-294-99-575

specialized application insole shoe orthotics for a patient with diabetes (ISO diabetes). As a result, these materials are gaining widespread acceptance in the footwear sector at this time because the industry can provide a lighter weight shoe with high comfort, robustness, and durability [9].

ISO diabetes used in footwear to reduce pain and mechanical load on the patient's leg would be better if manufactured using CNC machines. This machine produces ISO diabetes with high surface quality, accuracy, and precision. To generate an ISO product with these requirements, parameters need to be optimized on the optimal cutting CNC machine and its supporting equipment. The imprecise results of conventional foam box methods, which were carried out by several orthotics laboratories in Indonesia, can be minimized using reverse engineering, CAD, CAM, and CNC [6-7]. Surface quality and T_a initially ranging from $R_a = 20\text{--}30\text{ }\mu\text{m}$ and 1-week working time can be reduced to $R_a = 5\text{--}9\text{ }\mu\text{m}$ and five to seven hours/pair of orthotic shoes (ISO diabetes). To achieve this highly desirable result, the use of optimization techniques to determine precise machining parameter settings and obtain an optimal response is the research done in this paper. Two statistical methods were used to resolve this problem, Taguchi methodology (TM) and response surface methodology (RSM). These methods were used to help researchers and an ISO engineer solve the problems of determining the insole designs when EVA foam rubber is used.

The objective of this paper is to develop a mathematical model and optimize the manufacturing process parameters using the hybrid TM-RSM approach. This hybrid approach was chosen to develop a mathematical model and optimize the orthotic shoe insole cutting parameters in a CNC milling process on the EVA rubber foam material.

2. Methods

2.1. The 3D design of the shoe insole orthotics

Three types of orthotic shoe insole designs that fit the contour of diabetes mellitus patient's legs were manufactured on a CNC milling machine. According to the results of the work carried out previously [10], reverse innovative design (RID) methods were used to develop a 3D model shoe orthotic insole with the aid of 3D scanning (Handyscan 700TM) in which the surface modeling base curve of the three insole designs can be explored using the CAD software PowerSHAPE 2017. The results of insole design for precise geometric tolerances enlarged along the XY axis ranged from 0.75 to 1.50 mm. Three types of orthotics shoe insole designs that fit with the foot of patients who have were successfully obtained by previous researchers [5-6] and are shown in Fig. 1.




Fig. 1 Top view of 3D CAD model shoe insoles with several size tolerances

2.2. Condition cutting parameters and design of experiments

Six machining parameters were selected and evaluated, namely toolpath strategy (A), spindle speed (B), feed rate (C), step over (D), EVA foam with variable hardness (E), and the type of insole design with wide tolerance (F). Based on all machining parameters in Table 1, the optimal experiment design in this research used the Taguchi methods with Minitab v2017 was an orthogonal array OA $L_{27}3^6$ and is shown in Table 2.

Table 1 Parameter and their machining level for OA L₂₇3⁶

Factor	Level		
	1	2	3
A	Raster 90°	Raster 45°	Step and Shallow
B	14000 rpm	14500 rpm	15000 rpm
C	800 mm/min	850 mm/min	900 mm/min
D	0.20 mm	0.25 mm	0.30 mm
E	20–35 HRc (\$31/sheet)	40–50 HRc (\$37/sheet)	50–60 HRc (\$47/sheet)
F	0.50 mm	0.75 mm	1.00 mm

Table 2 Response data surface roughness (Ra) and Ta for OA L₂₇3⁶

N exp	Uncoded value of factor						Ra	Ra	Ta	Ta
	A	B	C	D	E	F	Insole patient 1	Insole patient 2	Patient 1	Patient 2
							μm	μm	Minutes	Minutes
1	1	1	1	1	1	1	7.671	8.594	323.32	336.39
2	1	1	1	1	2	2	8.995	9.436	319.40	334.45
3	1	1	1	1	3	3	9.252	8.081	321.80	333.83
4	1	2	2	2	1	1	6.969	7.716	256.44	269.35
5	1	2	2	2	2	2	8.011	8.800	254.24	268.34
6	1	2	2	2	3	3	8.368	6.618	254.20	268.52
7	1	3	3	3	1	1	7.812	8.027	214.96	229.95
8	1	3	3	3	2	2	8.324	9.286	212.77	229.77
9	1	3	3	3	3	3	8.527	8.319	213.89	229.80
10	2	1	2	3	1	2	7.162	7.881	229.52	245.17
11	2	1	2	3	2	3	8.198	9.225	228.58	244.57
12	2	1	2	3	3	1	8.080	7.496	227.78	243.88
13	2	2	3	1	1	2	7.967	8.395	301.10	315.20
14	2	2	3	1	2	3	9.330	8.771	298.35	313.75
15	2	2	3	1	3	1	7.659	8.897	297.52	312.44
16	2	3	1	2	1	2	8.432	7.557	276.97	290.96
17	2	3	1	2	2	3	7.934	7.361	274.80	289.85
18	2	3	1	2	3	1	8.417	6.890	272.55	288.78
19	3	1	3	2	1	3	7.963	8.151	273.59	289.62
20	3	1	3	2	2	1	8.588	9.061	321.67	337.44
21	3	1	3	2	3	2	8.822	7.970	270.45	283.65
22	3	2	1	3	1	3	8.165	7.983	271.33	286.35
23	3	2	1	3	2	1	7.974	7.881	326.90	343.99
24	3	2	1	3	3	2	7.554	8.047	267.33	282.33
25	3	3	2	1	1	3	8.009	6.850	327.28	341.77
26	3	3	2	1	2	1	7.599	8.489	382.09	398.11
27	3	3	2	1	3	2	8.372	9.008	322.65	338.53

Table 3 Response surface roughness (Ra) for S/N ratios (dB) and the Means effects (m)


Control factor	Surface roughness Ra (Insole patient 1)					Surface roughness Ra (Insole patient 2)				
	level 1	level 2	level 3	SN Ra	Delta	level 1	level 2	level 3	SN Ra	Delta
	Mean (μm)			(dB)	(μm)	Mean (μm)			(dB)	(μm)
A	8.214	8.095	8.131	26618.0	0.119	8.320	8.053	8.181	5637.1	0.267
B	8.304	8.158	8.011	4664.21	0.293	8.433	7.976	8.123	1848.7	0.456
C	7.863	8.277	8.332	1517.19	0.469	8.009	7.981	8.542	1004.9	0.561
D	8.317	7.989	8.167	3692.73	0.328	8.502	7.791	8.238	776.7	0.711
E	7.794	8.328	8.350	1007.68	0.556	7.906	8.701	7.925	487.28	0.795
F	8.193	7.863	8.443	1182.39	0.580	8.117	7.932	8.486	1260.	0.554

The average Ra for orthotic shoe insoles was measured with a Ra tester (Mark Surf PS 1) in Table 2, and the Ra value obtained is Ra value on average for the second leg of the patient. The response of processing time (Ta) and surface roughness (Ra) for S/N ratios and means effects are shown in Tables (3)-(4).


Table 4 Response processing time (Ta) for S / N ratios (dB) and the effects of Means (hours)

Control factor	Insole processing time (T _{A1})					Insole processing time (T _{A2})				
	(Patient 1)					(Patient 2)				
	level 1	level 2	level 3	SN Ra	Delta	level 1	level 2	level 3	SN Ra	Delta
	Mean (hour)			(dB)	(hour)	Mean (hour)			(dB)	(hour)
A	4.391	4.458	5.118	-12.73	0.727	4.630	4.707	5.374	-13.21	0.743
B	4.659	4.680	4.627	-13.13	0.054	4.906	4.926	4.879	-13.61	0.048
C	4.916	4.598	4.452	-12.87	0.463	5.156	4.848	4.707	-13.36	0.449
D	5.359	4.546	4.061	-12.09	1.298	5.601	4.784	4.326	-12.65	1.275
E	4.583	4.849	4.534	-13.05	0.316	4.824	5.106	4.781	-13.52	0.325
F	4.858	4.545	4.563	-13.08	0.313	5.112	4.793	4.806	-13.55	0.318

2.3. Material specimens, machine tools, and cutting tools specification



(a) Three types of EVA rubber foam with different hardness




(b) Insole product with various harnesses


Fig. 2 Research outputs

The EVA foam rubber size used in the experiments for insole manufacture in the CNC milling process was 250 mm x 95 mm x 23 mm. This material has a hardness in the range of 20–60 HRc, was measured by using a shore hardness tester (Asker CL-150). Three types of EVA foam rubber identified based on three hardness levels (Level 1 20–35 HRc, Level 2 35–45 HRc, and Level 3 50–60 HRc). The material prices for 1200 x 2400 x 30 mm sheets in the local market in Jakarta, Indonesia are presented in Table 1. Besides, EVA foam rubber also has a density of 55–65 kg/m³, the nominal size on the market of around 2000 x 1000 mm, thickness (separate) of 3–36 mm, the tensile strength of 800 kPa, and tear strength of 4.5 kN/m [2]. The test

CNC milling process on the EVA foam rubber made the used maximum spindle speeds up to 17,000 rpm and 100 W DC-power spindle motors. The used cutting tools were made from carbide milling cutter endmill type SECO [93060F] and ball-nose milling cutter [JS533060D1B0Z3 -NXT]. Material specimens, outputs, and a flowchart of the research are presented in Figs. (2)-(3).



(a) Experimental



(b) Optimization modeling with the hybrid approach to TM-RSM

Fig. 3 Manufacturing optimization flow diagram, ISO diabetes

3. Results and Discussion

In this study, the value of R_a was obtained from experiments varying the cutting parameters for the orthotic shoe insole manufacturing process in a Roland MDX 40R CNC machine, and the results are shown in Table 2. The effect or influence arising from any level of the factors on quality characteristics was analyzed using the signal-to-noise ratio. Different values of SNR between the maximum and minimum (main effect) are presented in Tables (3)-(4). For R_a of the shoe insole orthotics for Patient 2, the optimum value can be achieved if conditions are set at Level 2 for factors toolpath strategy (A), spindle speed (B), feed rate (C), depth of cut (D) and insole design type (F), while the EVA foam rubber hardness factor (E) is set at Level 1. Therefore, two cutting parameter optimal conditions for minimal R_a (orthotics shoe insole for Patients 1 and Patient 2 suffering from diabetes) can be simplified according to a combination of factors, $A_2B_3C_1D_2E_1F_2$ and $A_2B_2C_2D_2E_1F_2$ (Table 3). The optimal setting parameter $A_1B_3C_3D_3E_3F_2$ (Table 4) meant Level 1 for toolpath strategy (A); Level 3 for spindle speed (B), feed rate (C), depth of cut (D), as well as the type of EVA rubber foam (E); and Level 2 for the insole design (F). The results of this combination are presented in Tables (3)-(4), where the means and the SNR values with the quality characteristic of the Taguchi method are smaller, it can be proved better in this paper. The values of contributions (%) for the response R_a (insole for Patient 1 and Patient 2) respectively is 78.62% and 89.00% (with error 21.376% and 11.00%), while for the working time it is 99.98% and 100% on ANOVA (analysis of variance) in Tables (5)-(6). Furthermore, the percentage contribution to the linear model,

the square model, and the interaction between factors on Patient 1 of the Ra in Table 5 is 37.05% (linear), 15.24% (squares), and 15.13% (interaction between factors). Factor E and F contribute more significantly (17.20% and 17.04%), followed by Factor C (1.73%), B (1.21%), D (0.95%), and A (0.42%). Similarly, the ANOVA values for Ra for Patient 2 give the result that Factor C is the most effective factor, contributing 6.54%, followed by Factor F (2.29%), D (1.27%), E (0.59%), B (0.30%), and A (0.22%) are shown in Table 6. Correspondingly, Ra of the lowest orthotic shoe insole can be achieved by an optimum condition milling process (factors feed rate and the type of material EVA foam rubber), and also by the results of research work has been published [4, 11-12].

Table 5 ANOVA for surface roughness Ra for Patient 1

Variation of Source	DoF	SS	MS	F-value	P-value	Contribution (%)
Model	13	6.353	0.4887	3.68	0.013	78.62
Linear	6	2.994	0.4990	3.76	0.022	37.05
A	1	0.034	0.0339	0.26	0.406	0.42
B	1	0.098	0.0979	0.74	0.538	1.21
C	1	0.140	0.1402	1.05	0.323	1.73
D	1	0.077	0.0771	0.58	0.460	0.95
E	1	1.390	1.3901	10.5	0.007	17.20
F	1	1.377	1.3768	10.4	0.007	17.04
Square	2	1.232	0.6159	4.63	0.03	15.24
C*C	1	0.839	0.839	6.31	0.026	10.38
E*E	1	0.393	0.3930	2.96	0.109	4.86
2-Way Interaction	7	1.223	0.2791	2.1	0.130	15.13
A*B	1	0.127	0.127	0.96	0.346	1.57
A*C	1	0.290	0.0033	2.19	0.163	3.59
B*F	1	0.264	0.2638	1.99	0.182	3.26
C*E	1	0.509	0.5086	3.83	0.072	6.29
D*F	1	1.068	1.068	8.04	0.014	13.21
Error	13	1.727	0.1329			21.376
Total	26	8.081				100

Table 6 ANOVA for surface roughness Ra for Patient 2

Variation of Source	DoF	SS	MS	F-value	P-value	Contribution (%)
Model	16	8.8423	0.5526	5.06	0.049	89.00
Linear	6	1.1329	0.1882	1.73	0.212	11.40
A	1	0.0214	0.0214	0.2	0.668	0.22
B	1	0.0299	0.0299	0.27	0.612	0.30
C	1	0.6500	0.6501	5.95	0.035	6.54
D	1	0.1258	0.1258	1.15	0.309	1.27
E	1	0.0588	0.0588	0.54	0.480	0.59
F	1	0.2274	0.2274	2.08	0.180	2.29
Square	3	4.7855	1.5952	14.6	0.001	48.17
A*A	1	1.4859	1.4859	13.6	0.004	14.96
D*D	1	0.1969	0.1969	1.8	0.209	1.98
E*E	1	2.5920	2.5920	23.73	0.001	26.09
2-Way Interaction	7	3.09987	0.44284	4.05	0.023	31.20
A*F	1	1.15284	1.15284	10.55	0.009	11.60
B*E	1	0.2085	0.2085	1.91	0.197	2.10
B*F	1	0.2170	0.2170	1.99	0.189	2.18
C*D	1	0.3737	0.3737	3.42	0.094	3.76
D*F	1	0.2452	0.2452	2.24	0.165	2.47
E*F	1	0.29503	0.29503	2.7	0.131	2.97
Error	10	1.092	0.1093			11.00
Total	26	9.935				100.00

RSM was conducted in this paper for modeling and analyzing several variables that have a significant relationship between the dependent variable and one or more of the independent variables defined in the study. In this way, the experimental results of the EVA foam rubber milling process in CNC machines can be developed into a mathematical model with response Ra and Ta. The second-order regression model can be seen in Eqs. (1)-(4). This regression model is a function of six machining parameter variables (A, B, C, D, E, and F), which were set in Table 1, and can be expressed using RSM with Minitab software v17.

$$\begin{aligned} Ra_{(patient2)} = & 77.983 + 0.39A - 0.0186B + 0.133C + 134.941D - 8.016E - 0.217F \\ & + 0.0000119AB + 0.000679AC - 2.623AD + 0.0758AE - 0.325AF + 0.0000056BC \\ & - 0.0039BD + 0.000217B + 0.000368BF - 0.104CD + 0.00532CE - 0.00508CF \\ & + 0.1501DE + 13.582DF - 0.199EF - 0.1005A^2 + 0.00000049B^2 - 0.00012C^2 \\ & + 13.39D^2 + 0.069E^2 - 1.436F^2 \end{aligned} \quad (1)$$

$$\begin{aligned} Ra_{(patient1)} = & -104.433 - 0.155A + 0.0058B + 0.1403C + 168.123D + 0.726E + 1.104F \\ & + 0.000071AB - 0.00093AC + 1.682AD + 0.2AE + 0.0754AF - 0.00000116BC \\ & - 0.00445BD - 0.0000678BE - 0.00025BF - 0.0785CD - 0.000984CE \\ & - 0.0123CF - 1.245DE - 8.659DF + 0.27EF - 0.2548A^2 - 0.2548A^2 \\ & - 0.000000072B^2 - 0.000063C^2 - 69.614D^2 + 0.0504E^2 - 3.76F^2 \end{aligned} \quad (2)$$


$$\begin{aligned} Ta_{(patient1)} = & 5604.97 - 3.03A^2 - 0.000002B^2 + 0.00203C^2 + 4157.03D^2 + 0.017E^2 + 103.08F^2 \\ & - 97.395A - 0.25B - 8.18C + 85.5D + 1.36E - 27.33F + 0.015AB - 0.0163AC \\ & + 75.275AD + 0.083AE + 22.35AF + 0.00038BC - 0.13BD + 0.00019BE - 0.011BF \\ & - 0.651CD - 0.006CE - 0.006CF - 3.146DE + 226.42DF + 0.085EF \end{aligned} \quad (3)$$

$$\begin{aligned} Ta_{(patient2)} = & 2749.34 - 6.427A^2 - 0.0000037B^2 + 0.00176C^2 + 319.05D^2 + 0.0015E^2 + 133.45F^2 \\ & + 175.74A - 0.0507B - 6.125C + 2678.92D + 0.235E + 119.739F + 0.00107AB - 0.22AC \\ & + 32.8AD + 0.0775AE + 21.92AF + 0.00026BC - 0.227BD + 0.00018BE - 0.0132BF \\ & + 0.178CD - 0.002CE - 0.35CF - 7.51DE + 549.02DF + 0.471FE \end{aligned} \quad (4)$$


In this study, the response to Ra in both patients provides R² of 97.80% (Patient 1) and 98.20% (Patient 2). In this case, the value of R² was close to 100%, as desired for this experiment. Therefore, the two regression models that were formed above can be used to predict the Ra at certain design parameters.

For a better understanding of the interaction effect of all the machining variables on Ra, 3D-plot curves for the measured response can be developed using Eqs. (1)-(4). The 3D surface graphs illustrate the relationship between cutting parameters and the response Ra is shown in Figs. (4)-(5).


The predictability of the mathematical model developed by researchers was performed separately for each experiment, which provides the optimum Ra value for each insole right leg and left leg at 8.538 µm and 7.828 µm, respectively. The optimal Ra value has been obtained precisely and significantly to the optimal cutting conditions that have been set: toolpath strategy (raster machining 45°), spindle speed (14,500 rpm), feed rate (850 mm / min), step over (0.25 mm), EVA foam with hardness 20-35 HRc (Level 1), and the type of insole design with wide tolerance set on 0.75 mm. At these conditions, the value of Ra is predicted to follow a trend that is similar to the experimental value in the manufacturing process in the CNC milling machine with an average absolute percentage error for the second insole less than 3.6% (Tables 7-8) [11-13].




(a) Spindle feed-toolpath strategy for left foot of patient no. 1



(b) Spindle feed-toolpath strategy for right foot of patient no. 1




(c) Type material-feeding for left foot of patient no. 2




(d) Type wide tolerance-type of material for right foot of patient no. 2


Fig. 4 The 3D plot curve of surface roughness (Ra)




(a) Type EVA foam-Toolpath for left foot of patient no. 1



(b) Type design insole-Type EVA foam for right foot of patient no. 1



(c) Type EVA foam-Toolpath for left foot of patient no. 2



(d) Design insole-type Type EVA foam for right foot of patient no. 2

Fig. 5 The 3D plot curve of Time machining (Ta)

In this approach, the measured parameter of each predicted response can be transformed into a dimensionless desirability value (dF) [14]. The scale of the desirability function is between 0 and 1. If the value of DF = 0 or close to 0, the response is considered to be unacceptable. If the value of DF=1 or close to 1, the response is considered to be optimal.

A confirmation experiment was performed at the optimum conditions predicted and yielded Ra values of 8.432 μm and 7.557 μm (insole for Patient 1 and Patient 2, respectively) as well as Tm values of 213.89 min. and 229.80 min. (Table 7). The ability to successfully predict from the model also tested in optimal conditions. The predictive values of Ra = 8.538 μm and 7.828 μm were obtained from the model (Table 8). Optimal results obtained with different optimization techniques (TM and TM-RSM) were compared and there was a significant improvement in the surface which was finished with the hybrid approach. Predictive and comparative analyses of optimal conditions in this study are all summarized in Table 7. Based on the observations in Table 8, the hybrid approach of optimization techniques with TM-RSM provided 0.24% and 1.56% improvement of the surface finishing process for the same shoe orthotics insole compared with the optimal results obtained from the TM approach. The TM-RSM hybrid approach provides significant values for the absolute error of shoe orthotic insoles for the left leg and right foot for both patients with diabetes mellitus, 11.31%, and 4.85%, respectively the desirability function for the Ra shoe orthotic insoles of the left leg and right for both the patients are presented in Fig. 6.


Table 7 Optimum parameters and test results confirm the experimental results with predicted Ra and Ta values using the response surface method (RSM)

Optimal Cutting Parameters Conditions	Toolpath	Spindle Speed	Feed Rate	Step Over	Type of Material EVA	Width Tolerance	Ra_Based		Percentage Error (%)
		(RPM)	(mm/min)	(mm)	(HRc)	(mm)	Exp.	RSM	
							(μm)		
A ₂ B ₂ C ₂ D ₂ E ₁ F ₂	raster 45°	14,500	850	0.25	20–35	0.75	8.432	8.538	1.26
A ₂ B ₂ C ₂ D ₂ E ₁ F ₂	raster 45°	14,500	850	0.25	20–35	0.75	7.557	7.828	3.59
Optimal Cutting Parameters Conditions	Toolpath	spindle Speed	feed Rate	Step over	Type of Material EVA	width Tolerance	Ta_Based		Percentage Error (%)
		(RPM)	(mm/min)	(mm)	(HRc)	(mm)	Exp.	RSM	
							(μm)		
A ₁ B ₃ C ₃ D ₃ E ₃ F ₂	raster	15,000	900	0.3	50–60	0.75	213.89	216.56	1.25
A ₁ B ₃ C ₃ D ₃ E ₃ F ₂	raster	15,000	900	0.3	50–60	0.75	229.80	237.36	3.29

Table 8 Comparison of Ra optimum and experimental results

Optimization techniques	Ra					
	Optimal		predicted		Absolute % error	
	Patient 1	Patient 2	Patient 1	Patient 2	Patient 1	Patient 2
	(μm)	(μm)	(μm)	(μm)		
Taguchi Approach (TM)	7.554	7.332	6.936	6.752	8.18	7.68
Approach TM-RSM	7.572	7.448	8.538	7.828	11.31	4.85
Percentage (%) improvement	0.24	1.56	-	-		
Optimization techniques	Ta					
	Optimal		predicted		Absolute % error	
	Patient 1	Patient 2	Patient 1	Patient 2	Patient 1	Patient 2
	(minutes)	(minutes)	(minutes)	(minutes)		
Taguchi Approach (TM)	213.89	229.8	179.04	212.46	16.29	7.55
Approach TM-RSM	276.63	286.17	217	237.36	21.71	17.06
Percentage (%) improvement	22.68	19.70	-	-		

In the study, the desirability functions T_a was selected as "the smaller the better" because the optimal minimum T_a can be achieved in the machining parameters in the optimum CNC milling machine. The desirability functions of "the smaller the better" can be shown in Fig. 6, the patient's optimal value, T_{a1} , in the model was reached at 309.22 minutes, which gives a chance to the toolpath 2.09 (Levels 2–3), 14075.39 rpm spindle speed (Level 1), 936.88 mm/min feed rate (Level 3), 0.28 mm step over (Level 3), a material with hardness 76.67 HRc (Level 3), and the 0.82 design (Level 3). The optimal value for model T_{a2} patients was achieved at 286.098 minutes and was set at 2.15 (Levels 2–3), 14935.86 rpm spindle speed (Level 3), 859.88 mm/min feed rate (Level 3), 0.23 mm step over (Level 2), a material with hardness 11.01 HRc (level 1), and 0.75 design type (Level 2). The T_a desirability values for both patients reached values of 1.00. As a result, the response is considered perfect for the target value. The results of this paper had been proven by researchers [6-7, 15-16] in the process of design, manufacturing, and fabricating orthotic shoes comprising shoe last, the shoe insole and, special orthotics for diabetes patients.



(a) Surface roughness (Ra)

Profiles for Predicted Values and Desirability


(b) Machining time (T_a)

Fig. 6 Profile predicted values and desirability with TM-RSM hybrid methods

(D=composite desirability; d= individual desirability; High = highest value parameter; Cur = optimal current value of control parameter; Low = lowest value parameter, y = response parameter, Ra = average surface roughness; A = toolpath strategy; B= spindle speed; C= feed rate; D = step over; E = EVA foams with variable hardness; F = typical design of insoles with wide tolerance)

4. Conclusion

In this research, a TM_RSM approach was successfully implemented to create a mathematical model and optimize the milling process for ISO diabetes made of EVA foam rubber in a CNC milling machine. Based on the discussion mentioned earlier, the conclusions can be drawn as follows:

- (1) Ra at optimum cutting conditions based on the TM approach shows an optimum insole Ra value of 6.936 μm for Patient 1 and 6.752 μm for Patient 2. The optimal combination is in Position $A_2B_3C_1D_2E_1F_2$ and $A_2B_2C_2D_2E_1F_2$.
- (2) The optimum cutting conditions RSM-based approach shows the value of the surface roughness was $R_a = 7.828 \mu\text{m}$ (Patient 1) and $R_a = 8.538 \mu\text{m}$ (Patient 2), both were under the cutting parameters in $A_2B_2C_2D_2E_1F_2$.
- (3) The TM-RSM-based hybrid approach produces optimal machining parameter conditions at position: toolpath strategy (raster 45° and step & shallow machining), spindle speed (14,500–15,000 rpm), feed rate (800–900 mm / min), step over is 0.3 mm, the hardness of EVA foam material (20-35 HRc and 50-60 HRc), and ISO diabetes tolerance range (0.50 to 0.75 mm). The Ra optimum value of each was predicted at $R_a = 7.572 \mu\text{m}$ and $7.648 \mu\text{m}$ for the insole left leg and right leg, respectively.
- (4) The surface quality for the TM-RSM hybrid method is better than the other methods (0.24% for left foot insole and 4.13% for right foot insole) when compared to the optimum value of the Taguchi method.
- (5) Both methods (TM approach and TM-RSM approach) are very beneficial for data optimization of the results of CNC milling machine operation, which aims to reduce the time and cost of manufacture, to produce orthotic shoe insoles for a patient with diabetes.

Acknowledgment

We would like to gratefully thank you for PUTP Polytechnic ATMI Surakarta, Tribology Laboratory of the Department of Mechanical Engineering, University of Diponegoro in Semarang and CV EMA Pacific Surakarta that already provide full support in the form of infrastructure support CAM, CAD, and RE during the design, developed process as well as the writing of this paper.

This research was funded by Directorate of Research and Community Service, Directorate General of Research and Development Strengthening, Ministry of Research, Technology and Higher Education Fiscal Year 2019, grant Number: 257-93/UN7.P4.3/PP/2019 and Number: 257-73/UN7.P4.3/PP/2019. Letter of agreement for the implementation of research acceleration grants at the Atma Jaya University Yogyakarta, Number: 382/HB-PEN PGB/LPPM/XI/2019.

Conflicts of Interest

The authors declare no conflict of interest.

References

- [1] Y. P. Wu, Y. Ma, Y. Q. Wang, and L. Q. Zhang, "Effects of characteristics of rubber, mixing and vulcanization on the structure and properties of rubber/clay nanocomposites by melt blending," *Macromolecular Materials and Engineering*, vol. 289, no. 10, pp. 890-894, October 2004.
- [2] E. T. Nurit, W. Ety, H. F. Yifat, and G. Amit, "Role of EVA viscoelastic properties in the protective performance of a sport shoe: computational studies," *Journal Bio-Medical & Material Engineering*, vol. 16, no. 5, pp. 289-299, 2006.
- [3] Y. R. Jeng, S. Liu, and H-T. Yau, "Designing experimental methods to predict the expansion ratio of EVA foam material and using finite element simulation to estimate the shoe expansion shape," *Material Transactions*, vol. 53, no. 9, pp. 1685-1688, September 2012.

- [4] P. W. Anggoro, B. Bawono, A. Widiyanto, Jamari, and A. P. Bayuseno, "Parameter optimization of strategies at the CNC milling machines rolland model MDX 40R cam surface roughness against shoe orthotic insole made of EVA foam rubber," *International Journal of Mechatronics and Mechanical Engineering*, vol. 6, no. 4, pp. 96-104, 2016.
- [5] P. W. Anggoro, E. Saputra, M. Tauviquirrahman, Jamari, and A. P. Bayuseno, "A 3-dimensional finite element analysis of the shoe insole orthotics for foot deformities," *International Journal of Applied Engineering Research*, vol. 12, no. 15, pp. 5254-5260, 2017.
- [6] P. W. Anggoro, M. Tauviquirrahman, Jamari, A. P. Bayuseno, B. Bawono, and M. M. Avellina, "Computer-aided reverse engineering system in the design and production of orthotic insole shoes for patients with diabetes," *Cogent Engineering*, vol. 5, no. 1, pp. 1-20, June 2018.
- [7] P. W. Anggoro, M. Tauviquirrahman, Jamari, A. P. Bayuseno, J. Wibowo, and Y. D. Saputro, "The optimal design and manufacturing of shoe last product for an ankle foot orthotic for the patient with diabetes," *International Journal of Manufacturing, Materials, and Mechanical Engineering*, vol. 9, no. 2, pp. 62-80, April 2019.
- [8] M. Pracella, Minhaz-Ul Haque, and V. Md. Alvarez, "Functionalization, compatibilization, and properties of polyolefin composites with natural fibers," *Polymers Journal*, vol. 2, no. 4, pp. 554-574, November 2010.
- [9] Y. Shimazaki, S. Nozu, and T. Inoue, "Shock-absorption properties of functionally graded EVA laminates for footwear design," *Polymer Testing*, vol. 54, pp. 98-103, July 2016.
- [10] X. Ye, H. Liu, L. Chen, Z. Chen, X. Pan, and S. Zhang, "Reverse innovative design - an integrated product design methodology," *Computer Aided Design*, vol. 40, no. 7, pp. 812-827, August 2008.
- [11] M. Sarikaya and A. Gullu, "Taguchi design and response surface methodology-based analyses of machining parameters in CNC turning under MQL," *Journal of Clean Production*, vol. 65, pp. 604-616, 2014.
- [12] I. Asiltürk and S. Neseli, "Multi-response optimization of CNC turning parameters via Taguchi method-based response surface analysis," *Measurement*, vol. 45, no. 4, pp. 785-794, January 2012.
- [13] R. N. Yadav, "A hybrid approach of taguchi-response surface methodology for modeling and optimization of duplex turning process," *Measurement*, vol. 100, pp. 131-138, January 2017.
- [14] A. N. Sait, S. Aravindan, and A. N. Haq, "Optimization of machining parameters of glassfibre-reinforce plastics analysis technique using Taguchi," *International Journal of Advanced Manufacturing Techniques*, vol. 43, pp. 581-589, 2009.
- [15] B. Bawono, P.W. Anggoro, M. Tauviquirrahman, A. P. Bayuseno, and Jamari, "The Evaluation of the Use of AFO (ankle foot orthotics) with the MOXFQ (manchester-oxford foot questionnaire) method," *Atlantis Highlights in Engineering*, vol. 1, pp. 657-662, 2018
- [16] P. W. Anggoro, B. Bawono, M. Tauviquirrahman, A. P. Bayuseno, and Jamari, "Design and manufacturing orthotics shoe insole with optimum surface roughness using the CNC milling," *Journal of Engineering Science and Technology*, Vol. 14, No. 4, pp. 1799-1819, 2019.



Copyright© by the authors. Licensee TAETI, Taiwan. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY-NC) license (<https://creativecommons.org/licenses/by-nc/4.0/>).